

G10-BR

- Wide usage resin for General purposes



Keywords

- High Definition
- Superior surface finish
- Easy to use and post-processing

Color	Brown
Density(g/cm ³ , 경화후)	1.12~1.18
Tensile Modulus(MPa)	2589~2695 MPa
Tensile Strength(MPa)	38~56 MPa
Elongation at Break (%)	12~20%
Flexural Strength(MPa)	69~74 MPa
Flexural Modulus(MPa)	2692~2775 MPa
HDT (°C, @66psi≈0.45MPa)	39~52°C

Characteristics

- Mock-up & Prototyping
- Sculptures & Figures
- Mass Productions
- Workability
- Impact resistance
- High detail and textured parts
- Cost-effective solutions
- Quick Production

www.glucklab.com

The characteristics of these products may differ according to environments of 3D printer and specific factors in software, post processing conditions, product application, operating conditions, or with end use. Specifications subject to change without notice.

© 2022 by Gluck, Inc. All rights reserved.

GLUCK 글럭